

DZ350 (MS)

Backsheet for Solar Module



Material

- PVDF
- Adhesive
- PET
- PE

Introduction:

This product can completely block the water vapor and oxygen. It also has excellent good electrical insulation and Anti- contamination ability. The outer PVDF fluorine membrane effectively block all ultraviolet rays. Under high temperature and high humidity.

There is no hydrolysis phenomenon. It is highly suitable for solar cell assembly encapsulation for high temperature and high humidity environment.

Specifications:

Item		Unit	Test Standard	Value
Back Film Thickness	Standard Thickness	μm	Micrometer	350
	Tolerance	--	Micrometer	±5%
Tensile Strength (MD)		N/mm ²	ASTM D-882-2009	≥110
Tensile Strength (TD)		N/mm ²	ASTM D-882-2009	≥100
Elongation at Break (MD)		%	ASTM D-882-2009	≥80
Elongation at Break (TD)		%	ASTM D-882-2009	≥80
Thermal Shrinkage (150°C×30min) (MD)		%	ASTM D-1204-2007	≤1.5
Thermal Shrinkage (150°C×30min) (TD)		%	ASTM D-1204-2007	≤1.0
Adhesion Release between layers		N/cm	ASTM D-3359-2002	≥5.0
Adhesion with EVA (Initial)		N/10mm	ASTM D 1876	≥40
Breakdown Voltage		KV	ASTM D 149-1997	≥18
Partial Discharge		VDC	IEC 60664-1-2007	≥1000
Water Vapor Transmission Rate		g/m ² ·d	ASTM F 1249-2006	≤2.5
Ageing Test (85°C×85%RH,1000h)		--	IEC 61215-2005	No Delamination, No Bubbles, No Wrinkles Δb≤3.0
UV Pretest		--	IEC 61215-2005	No Delamination, No Bubbles, No Wrinkles Δb≤3.0
Salt Spray Test		--	IEC 60068-2-11:1981	No Delamination, No Bubbles, No Wrinkles
Boiling Test (Boiling Water for 24h)	Visual Inspection	--	GB/T 9286-1998	No Delamination, No Bubbles, No Wrinkles
	Peel strength btw layers	N/cm		≥4
Temperature Cycle Test (-40°C~85°C,50 Cycles)	Visual Inspection	--	IEC 61215-2008	No Delamination, No Bubbles, No Wrinkles
	Breakdown voltage	KV	GB/T 2423.3-2006	≥15
Freezing Cycle Test (-40°C~85°C,85%,10 Cycles)	Visual Inspection	--	IEC 61215-2008	No Delamination, No Bubbles, No Wrinkles
	Breakdown Voltage	KV		≥15

Disclaimer:

The technical information, recommendations and other statements contained in this document are based upon tests or experience that MSi believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond MSi's control and uniquely within user's knowledge and control can affect the use and performance of the product in a particular application. Given the variety of factors that can affect the use and performance of the product, user is solely responsible for evaluating the product and determining whether it is fit for a particular purpose and suitable for user's method of application.